



## TEST REPORT ON SCRATCH RESISTANCE

Client	Hesse Lignal Middle East, Dubai, UAE		
Sample Description	Cross coat DE 48774 Hesse Fantastic Clear	Lab Report No.	WD-R-211108-0488
Source	Hesse Lignal Middle East	Sample No.	WD-S-211108-0455
Wimpey Ref.	211108-06	Request No.	WD-Q-211108-0132
Test Method	ASTM D7027-20	Date Received	08/11/2021
Sample brought in by	Client	Date Tested	11/11/2021
Temperature & Relative Humidity	23°C & 50%	Date Reported	11/11/2021
Tested By	AV	Sampling Date	N.G

### Test Result

Test	Observation	Result
Scratch Resistance	The tested sample did not show any scratch when tested at a load of 400g	Resistant

Remarks: None

Signed for and on behalf of Wimpey Laboratories

S. Sarath Kumar  
Head of Department

Test results relate only to the samples tested.

This report shall not be reproduced except in full, without the written approval of the laboratory.

-End of text-

